

MULLITE

PURITY - CHEMICAL STABILITY

Characteristics


> Mullite ($3\text{Al}_2\text{O}_3 - 2\text{SiO}_2$) is a material known for offering key benefits such as:

- High strength and toughness
- Thermal shock resistance
- Low thermal expansion
- Low thermal conductivity
- Lightweight (compared to other ceramics)
- Electrical insulation
- Refractoriness
- Good chemical stability
- Good dielectric transparency


> To further enhance these advantages, Baikowski® has been developing **high phasic purity mullites**, available in **slurries and spray-dried powders**, that feature:

- Specific surface area (SSA): **35 m²/g**
- Particle size: **<0.2 μm**

Slurry - 50 wt% - pH 8.5 - PSD (Horiba)



Spray dried powder - PSD (Horiba – dry way)



Applications

> Baikowski® can design tailored mullite solutions, specifically incorporating nano-zirconia doping, to meet the requirements of advanced applications.



COATING



CMC



TECHNICAL CERAMICS



PRODUCT DESIGN

Any particular process issue? Let us know your requirements and we will design, together, the best solution for your needs.



With great powder comes great responsibility



Baikowski® 

©BAIKOWSKI® A/2026/EN

Baikowski® SA
France | Poisy | ☎ +33 4 50 22 69 02

Mathym® SAS
France | Lyon | ☎ +33 4 78 83 72 93

Baikowski® Malakoff Inc.
USA | Malakoff (TX) | ☎ +1 903-489-1910

Baikowski® International Corp.
USA | Charlotte (NC) | ☎ +1 704-587-7100

www.baikowski.com
sales@baikowski.com



Follow us:   

Sales Representative in China
China | Shanghai | ☎ +86 21.6289.2883

Baikowski® Korea Co, Ltd.
Korea | Seoul | ☎ +82 255.281.97

Baikowski® Japan Co, Ltd.
Japan | Chiba | ☎ +81 474.73.8150

The information and data contained in this document are based on tests believed to be reliable and are indicative only. They are given to demonstrate the typical values attached to every single product in the range, but should under no circumstance be considered as a formal commitment. Depending on the measurement methods and/or instrumentation, the results may vary from information provided herein. Baikowski® and its related companies (subsidiary and affiliated companies) are neither responsible nor liable for results obtained from the use of the products. Because of numerous factors affecting results, Baikowski® makes no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Each purchaser must conduct its own testing for safety and regulatory evaluations. **Baikowski SA reserves the right to change the information given herein without prior notice.**